

- 24 -

CLAIMS

5

1. A method of fabricating a semiconductor device, comprising the steps of:

forming a first insulation film on a substrate by a spin-on process;

10 applying a curing process to said first insulation film at a temperature of 380 - 500°C over a duration of 5 - 180 seconds; and

forming a second insulation film on said first insulation film by a spin-on process.

15

2. A method as claimed in claim 1, wherein  
20 said first insulation film comprises an organic material having a specific dielectric constant of 3.0 or less.

25

3. A method as claimed in claim 1, wherein  
said first insulation film comprises an organic  
material of aromatic group.

30

- 25 -

4. A method as claimed in claim 1, wherein  
said first insulation film is formed of a spin-on  
film selected from the group consisting of an SiNCH  
film, an SiOCH film, an organic SOG film, and an HSQ  
5 film.

10 5. A method as claimed in claim 1, wherein  
said second insulation film comprises an organic  
material having a specific dielectric constant of 3.0  
or less.

15

6. A method as claimed in claim 1, wherein  
said second insulation film comprises an organic  
20 material of aromatic group.

25 7. A method as claimed in claim 1, wherein  
said second insulation film is formed of a spin-on  
film selected from the group consisting of an SiNCH  
film, an SiOCH film, an organic SOG film, and an HSQ  
film.

30

- 26 -

8. A method as claimed in claim 1, wherein said curing process is conducted at a temperature between 380 - 500°C over a duration of 10 - 150 seconds.

5

9. A method as claimed in claim 1, wherein  
10 said curing process is conducted at a temperature between 400 - 470°C over a duration of 10 - 150 seconds.

15

10. A method as claimed in claim 1, wherein said curing process is conducted such that there is formed an intermixing layer between said first and  
20 second insulation films.

25 11. A method of fabricating a semiconductor device, comprising the steps of:

forming a first insulation film on a substrate by a spin-on process;

30 applying a curing process to said first insulation film at a temperature of 380 - 500°C over a duration of 5 - 180 seconds;

forming a second insulation film on said first insulation film by a spin-on process;

- 27 -

patterning said second insulation film to form an opening therein; and

etching said first insulation film while using said second insulation film as a mask.

5

12. A method as claimed in claim 11,  
10 wherein said first insulation film comprises an organic material having a specific dielectric constant of 3.0 or less.

15

13. A method as claimed in claim 11,  
wherein said first insulation film comprises an organic material of aromatic group.

20

14. A method as claimed in claim 11,  
25 wherein said first insulation film is formed of a spin-on film selected from the group consisting of an SiNCH film, an SiOCH film, an organic SOG film, and an HSQ film.

30

15. A method as claimed in claim 11,

- 28 -

wherein said second insulation film comprises an organic material having a specific dielectric constant of 3.0 or less.

5

16. A method as claimed in claim 11,  
wherein said second insulation film comprises an  
10 organic material of aromatic group.

15 17. A method as claimed in claim 11,  
wherein said second insulation film is formed of a spin-on film selected from the group consisting of an SiNCH film, an SiOCH film, an organic SOG film, and an HSQ film.

20

18. A method as claimed in claim 11,  
25 wherein said curing process is conducted at a temperature between 380 - 500°C over a duration of 10 - 150 seconds.

30

19. A method as claimed in claim 11,  
wherein said curing process is conducted at a

- 29 -

temperature between 400 - 470°C over a duration of 10  
- 150 seconds.

5

20. A method as claimed in claim 11,  
wherein said curing process is conducted such that  
there is formed an intermixing layer between said  
10 first and second insulation films.

15